

**TIF700HZ Series** thermally conductive interface materials are applied to fill the air gaps between the heating elements and the heat dissipation fins or the metal base. Their flexibility and elasticity make them suited to coat very uneven surfaces. Heat can transmit to the metal housing or dissipation plate from the heating elements or even the entire PCB, which effectively enhances the efficiency and life-time of the heat-generating electronic components.

**Typical Properties of TIF700HZ Series**

Color	Blue	Visual
Construction	Ceramic filled silicone elastomer	*****
Thickness range	0.020"-0.200"	ASTM D374
Hardness	25 Shore 00	ASTM D2240
Specific Gravity	3.3 g/cc	ASTM D297
Operating Temp	-40 ~160 °C	*****
Dielectric Breakdown Voltage	5.5 KV	ASTM D149
Dielectric Constant@1MHz	4.5 MHz	ASTM D150
Volume Resistivity	5.2X10 <sup>13</sup> Ohm-cm	ASTM D257
Thermal Conductivity	7.0 W/mK	ASTM D5470
	7.0 W/mK	GB-T32064
Outgassing (TML)	0.30%	ASTM E595
Flame Rating	UL94 V0	UL E331100


**Features**

- » Good thermal conductivity: 7.0 W/mK
- » Naturally tacky needing no further adhesive coating
- » Soft and Compressible for low stress applications
- » Available in varies thickness


**Application**

- » Cooling components to the chassis of frame
- » Set Top Box
- » Car Battery & Power Supply
- » Charging Pile
- » LED TV/ Lighting
- » Graphics Card Thermal Module

**kg. vs. Thermal Resistance**



**Psi. vs. Compression Ratio**



**Product Specification**

**Product Thicknesses**


0.020-inch to 0.200-inch (0.5mm to 5.0mm)

**Product Sizes**

10" x 16" (254mm x 406mm)

Individual die cut shapes and custom thickness can be supplied. Please contact us for confirming.

**Product Identification:**



Thermal Conductive Interface Materials  
Application Technology Download

Thermally Conductive Materials    Heat Generating Materials    Thermally Conductive Plastics  
Foaming Silica Gel    Die-Cutting Products

**Canada:**  
Tel: +001-604-2998559  
E-mail: sales@thermazig.com

**China:**  
Tel: +86-769-38801208  
E-mail: frances@ziitek.com

**Taiwan:**  
Tel: +886-2-22771007  
E-mail: frances@ziitek.com.tw



The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.

http://www.ziitek.com